



---

## Polishing Soap

---

Product Information 199

---

### GENERAL:

Marseille Soap dates back to the 17<sup>th</sup> century, where - at Marseille/France – it was first produced. The very same recipe is still used today. Tree oils, especially olive oils, are the main ingredients.

**Marseille Polishing Soap** is used as a finishing coat on Venetian Plaster (Stuccolustro) work as well as on Tadelakt work. It will finish to a high gloss when polished and - as it reacts chemically with the base material – leaves a surface that is damp proof and resistant to dirt.

### PROPERTIES:

- ★ Transparent
- ★ High gloss
- ★ Hydroscopic
- ★ Dirt repellent
- ★ Plant based
- ★ Solvent free (solvent is water)

### INGREDIENTS:

Marseille Soap (Olive oil soap), limewater, Diatomaceous Earth.

### APPLICATION:

**Stuccolustro:** After a drying time of approx. 1-2 hours, apply **Polishing Soap** evenly with a wide and soft brush. Polish by using a hot trowel. Recommended is a Venetian Trowel (Prod.No: K4220 or K4224) heated to approx. 60-80deg.C For heating use a heat gun or a hotplate. Re-heat at short intervals to keep temperature even. The use of 2 Venetian Trowels is recommended, as one trowel can be re-heated while working with the other one.

**Tadelakt:** After a drying time of approx. 1-2 hours, apply **Polishing Soap** evenly with a wide and soft brush. For polishing a special stone is used – see info **TADELAKT**.

### CLEANING TOOLS:

Immediately after use with warm water.

### COVERAGE:

Approx. 50g / 1sqm

### PACKAGE SIZES:

Prod. No: 199 0,75kg

Prod. No: 200 2,5kg

For prices see the latest price list

### STORAGE:

Stored dry, cool and frost-free **POLISHING SOAP** may be kept for at least 12 months.

### MARKINGS:

None, no dangerous material

### DISPOSAL:

Dispose of with household waste or better use up by cleaning paint brushes.

### SAFETY WARNING:

Avoid contact with eyes. In case of eye contact wash immediately with plenty of water, also under the eyelids.

**Keep out of reach of children**

### NOTE:

**Since STUCCOLUSTRO and TADELAKT work require a high degree of craftsmanship, we strongly recommend attending one of our STUCCOLUSTRO / TADELAKT workshops / seminars.**

The above information has been compiled in accordance with the best of our experience and knowledge. Owing to the application methods and environmental influences, as well as the various surface properties, no liabilities or legalities pertaining to the individual recommendations can be entertained. Prior to application, the suitability of the product is to be tested (trial coat). The validity of the text ceases with revisions or product modifications.

(07/2003)

---

Mike Wye & Associates  
Buckland Filleigh Sawmills  
Beaworthy  
Devon EX21 5RN

---

Tel: 01409-281644  
Fax: 01409-281669  
E-Mail: sales@mikewye.co.uk  
Web Site: www.mikewye.co.uk