

# Mike Wye & Associates

## Suppliers of Natural Building and Decorating Products

- Phone us on 01409 281644
- E-mail us by clicking on [sales@mikewye.co.uk](mailto:sales@mikewye.co.uk)
- Write to us at Buckland Filleigh Sawmills, Buckland Filleigh, Devon EX21 5RN, England.

## CLAYTEC UNDERCOAT PLASTER

### Technical Information Sheet

**Description** **Claytec Undercoat** is a blend of clay, fine aggregate and plant fibres supplied as a dry powder. It has an indefinite shelf life if stored dry and requires only mixing with clean water to be ready for use. It hardens by drying - no chemical reaction takes place – and so remain workable for a long time and can be re-worked by the addition of water at any time.

Quality of the product is monitored by tests carried out by the manufacturer :

Tests of physical properties to ensure suitability of clay and aggregates.

Tests to ensure uniformity and performance of the batched product.

**Claytec Undercoat** and self-coloured plasters are available in the following quantities :

Product	Bag Weight kg	No. of bags/pallet	Recommended coat thickness mm	Yield m <sup>3</sup> /bag	Coverage m <sup>2</sup> /bag
Undercoat	30	42	15 - 50	0.023	1.5 - 0.45

**Design** **Claytec Undercoat** is suitable for use on internal surfaces of walls and ceilings. It attaches by mechanical bonding to all stable and dry substrates, including masonry, clayboard, reedboard, timber lathing and lime undercoat plasters. Undercoat plasters are not recommended for use on plasterboards because during drying, water will be absorbed by the board which will then become unstable.

It is a practical alternative to using gypsum or lime plasters and are compatible with 'breathing' construction in historic and new buildings.

**Claytec Undercoat** plaster can withstand minor movements of the background material without cracking. However the plaster should be reinforced when there is a possibility of structural movement or if different backgrounds are being covered.

**Physical Properties**

Density	1500 kg/m <sup>3</sup>
Thermal conductivity (k)	0.66 W/mK
Vapour diffusion resistance factor (ref air)	m8

<b>Resistance to Damage</b>	<p>Precautions common to good construction practice should be taken to avoid damage to the new plaster before completely dry.</p> <p>Corners should not be reinforced with metal beading as this will lead to differential wear of the softer plaster. They should be slightly rounded (2mm radius or greater) to reduce the risk of damage.</p>
<b>Resistance to Moisture</b>	<p>The plaster will deteriorate if applied onto damp backgrounds or if used unprotected in damp environments. Careful attention to detail is required in kitchens, bathrooms, shower areas, etc.</p> <p>Contact the supplier for advice on particular applications.</p>
<b>Resistance to Fire</b>	<p>Clay plaster is non-combustible.</p>
<b>Resistance to Moisture</b>	<p>The plaster will deteriorate if applied onto damp backgrounds or if used unprotected in damp environments. Careful attention to detail is required in kitchens, bathrooms, shower areas, etc.</p> <p>Contact the supplier for advice on particular applications.</p>
<b>Thermal/Moisture Movements</b>	<p>Clay plaster is dimensionally stable when used in dry internal conditions and as part of a 'breathing' wall construction.</p> <p>Plant fibres in undercoat plaster act as reinforcement and create voids thus controlling cracking due to drying shrinkage and thermal movements. The dried plaster is less brittle than conventional plasters and can withstand small movements of the substrate.</p>

**DIRECTIONS:**

**Mixing**

Add the dry plaster gradually to clean water in a large bucket using a plasterer's wheel or drill attachment to ensure even mixing.

The consistency should resemble conventional lime or gypsum plasters, i.e. not so dry and sticky that it cannot be spread nor so wet that it cannot be applied.

**Application**

**Clay undercoat** plaster can be applied using tools and techniques common to conventional lime and gypsum plasters. It is also suitable for use with plaster spraying machines.

Surfaces to be plastered should be stable, dust-free and lightly dampened before applying plaster. Smooth surfaces should be keyed using a spatter coat of plaster slurry or a brushed on primer mixed with sand. Reed mats can also be fixed to solid surfaces or over timber beams to provide a key. When reed mats and timber laths are used as a key, they should not be pre-wetted.

Undercoat can be applied in a single layer of up to 50mm thickness as a maximum for small areas, to 20mm thickness for larger areas. Finished thicknesses greater than 50mm should be applied in 25mm thick layers with a continuous layer of reed mat as reinforcement between the bottom two layers and a continuous layer of jute mesh reinforcement between outer layers.

Undercoats should be well keyed to provide a mechanical bond with subsequent layers which can be applied as soon as the previous layer is firm. The surface of each undercoat layer should be reinforced with a continuous layer of jute mesh when the area to be plastered consists of different backgrounds or when basecoat is applied on

lightweight or flexible backgrounds.

When patching, the edges of the area to be joined should be well wetted. Finish plasters can be applied as soon as the undercoat has dried and shrinkage is complete.

### **Drying**

Drying times vary considerably with the ambient conditions, applied thickness and the suction of the background. In ideal conditions, a 15mm thick undercoat will be dry after 3 - 4 days.

To encourage controlled drying, ensure plastered areas are well ventilated. In damp conditions a low heat and a de-humidifier may be required. Excess heat or forced ventilation may cause cracking. If cracking occurs, the affected area can be wetted and re-trowelled.

If drying is prolonged moulds may form on the straw. To prevent these use a gentle source of heat and/or a fan and a dehumidifier. The moulds will disappear when the plaster dries. They will not affect the plaster finish, nor will they reoccur.

Some cracks may appear as thicker coats of undercoat plaster dry. These are harmless but each coat should be allowed to dry before applying further coats.

### **Site Notes**

**Claytec Undercoat** plaster is supplied in paper sacks that can be broken by rough handling. They should be stored off the ground and protected from damp.

### **Health and Safety**

There is a small risk of inhalation of dust when handling clay plaster in the dry state. Clay plaster is non-irritant in contact with exposed skin.