

MIKE WYE & Associates Ltd

Suppliers of Natural Building and Decorating Products

sales@mikewye.co.uk Telephone: 01409-281644



Lime Mortar – Unhaired

Our coarse unhaired lime mortars are mixed at a 3/1 (sand : lime) ratio and are suitable for float coats, bedding & pointing.

The lime putty mortar is delivered in a pre-mixed state. The mortar is available in 20kg Tubs and 500kg, 900kg & 1000kg Bulk Bags.

The product is made of well graded sharp washed pit sand mixed with a lime putty binder. Our lime putty is made from a refined high calcium quicklime (CaO) that has been slaked and left to mature for a minimum of three months.

Specifications:

Please see below the standards that our raw materials conform to:

Sand: 0-4mm Sand EN12620 or BS882

Lime: BS EN 459-1 : 2001

Soundness test (totally slaked) - pass

PATS test (moisture content/maturity) - pass

99.99% is finer than 0.18mm particle size

Aggregate Grading:

| BS Sieve | Coarse Sand 1 (% Retained) | Coarse Sand 2 (% Retained) |
|---------------|----------------------------|----------------------------|
| >5mm | 0.00% | 0.00% |
| <5mm > 2.8mm | 1.00% | 3.00% |
| 2.8mm > 2mm | 6.00% | 8.00% |
| <2mm > 1mm | 12.00% | 26.00% |
| <1mm > 500μ | 25.00% | 24.00% |
| <500μ > 250μ | 31.00% | 15.00% |
| <250μ > 63μ | 25.00% | 24.00% |
| Total: | 100.00% | 100.00% |

Safety:

Limes are caustic. Always wear eye protection and protective gloves and clothing and follow the safety instructions on the labels.